









CHARACTERISTICS
-----------------

#### **INDOOR**

Composition:	Topcoat : 70,2% PVC, 7,8% PU
Backing:	21,9% Polyester
Weight:	730 gr/m²
Roll Width:	min. 137 cm
Roll Length:	+/- 30 m
Abrasion:	>100.000 cycles (MARTINDALE)
Cold Crack:	CFFA 6a-2010 no cracking
Accelerated-ageing tests:	(Tropical test ISO 1419): week 7: No cracking, peeling, or delamination
Light fastness:	>6 EN ISO 105B02 (Blue Wool Scale)
Colour fastness to	
Rubbing (dry):	4-5 EN ISO 105X12:2002 (Blue Wool Scale
Rubbing (wet):	4-5 EN ISO 105X12:2002 (Blue Wool Scale

US CAL TB 117-2013, Section 1: PASS

**UFAC Class 1** 

US NFPA 260 Cigarette ignition resistance ASTM E1353-08ae1: PASS class 1

US Surface Burning Characteristics of **Building Materials** ASTM E84-15B: class B

\*This term and any corresponding data refer to the typical performand should not be construed to imply the behaviour of this or any other m

### **FINISHES AND TREATMENTS**

PHTHALATE.

# **SUSTAINABILITY**

Flame retardancy\*:

Fire Resistant Additives Free Phthalate Free REACH RoHS

#### CARE AND CLEANING ⊠ 🖄 🕸 🖾 🔀

For optimum care and cleaning please read the following instructions and recommendations.

#### **Disinfectant Use**

For leather surface, use 1:250 mix of 84(NaClO) and water.

Rinse the area with clean water, then dry with a clean, lint-free cloth after using any disinfectants and cleaners.

#### Cleaning after Disinfection:

The coated fabric should be cleaned periodically in order to maintain its appearance and prevent build-up of dirt and contaminants. Any stain, spills, or soiling should be cleaned up immediately to prevent the possibility of permanent staining.

Use a mixture of 1:1 liquid soap (neutral pH) and water or our approved cleaning products for coated fabrics to remove stains on the surface of the material. Completely remove excess cleaner with a white, clean, damp cloth; and dry the surfaces afterwards. Lacquers, strong cleaners, detergents, bleach, xylene-based solutions, acetone, or ketone (MEK) cause immediate damage and contribute to the deterioration of the material. The use of such cleaners is at the owner's risk.

# Cleaning methods to remove tougher stains

Step 1: Coffee, juice, red wine, sauces, chocolate, grease, crayon and suntan lotion. Remove excess spill with a damp cloth. Clean with a 1:1 mix of neutral liquid soap and water. Next, rinse with clean water and dry.

Step 2: Make-up. Use a straight application of neutral PH soap. Wipe with a clean white cloth or soft brush, rinse with clean water, and dry.

Step 3: Blood, urine, faeces and all other tough stains. Use a 1:10 mix of Isopropyl alcohol and water. Rinse thoroughly with clean water and dry.

For cleaning: use a soft white cotton cloth saturated with the recommended cleaning agent and rub the stain in random circles, ten times or more. Pat dry with another soft white cotton cloth and check the results. Do not use steel bristle brushes, abrasive scouring pads or metal, these cause permanent damage to the fabric. Methods 2 & 3 are not recommended for everyday cleaning! After cleaning, rinse the area with clean water, then dry with a clean, lint-free cloth. Failure to remove chemical residue will cause discolouration of the coated fabric surface to manifest itself earlier in the life cycle of the product.

## **SAMPLES AND ENQUIRES**

samples: samples@vyvafabrics.nl | orders: info@vyvafabrics.nl







INFO@VYVAFABRICS.NL









TEL +31 (0)20 6599523